



TK-BRIGHT GLAZE

High Gloss Curing and Sealing Compound

Item No. TK-BR.GLAZE

PRODUCT DESCRIPTION

TK-BRIGHT GLAZE is a blend of 100% methyl/methacrylate polymers used as a superior and specialized compound for curing and sealing exposed aggregate, stamped/stenciled concrete and other decorative concrete and masonry surfaces. Formulated with higher viscosity (thickness) than standard curing and sealing compounds, TK-BRIGHT GLAZE is for applications where a glossier, one-coat finish is desired.

Features:

- Coating dries clear and does not yellow with age or exposure to ultraviolet rays.
- Provides superior protection against freeze/thaw cycles, deicing salts, and chemical erosion and efflorescence.
- Reduces the possibility of aggregate popouts on exposed aggregate by percolating down and around the stones to fill gaps and voids.
- Forms a durable long-lasting film with resistance to water, chemicals, abrasion and stains.
- Highlights and preserves the natural pigments in the surface, adding longevity and sparkle to the finished product.
- Does not discolor with over-use.

USES:

Suitable for interior or exterior use on new or existing architectural concrete, burnish block, terrazzo, brick, stone, slate, quarry tile or other cementitious materials. Ideal for exposed aggregate and colored concrete surfaces, paving block, patio stone, driveways and garage floors.

APPLICATION PROCEDURES:

PREPARATION:

Surfaces must be clean, dry and free of form oils, grease, dust, frost and curing compounds (particularly wax based). Large areas may be blown dust free by compressed air, washed and let dry. Surface water must be allowed to completely dissipate before applying.

Exposed Aggregate Application Preparation - When applying to exposed aggregate as a curing compound, the surface should be washed with a mild acid solution to remove the thin film of cement dust, then flushed with water and allowed to dry before applying TK-BRIGHT GLAZE.

At this point a small mock-up area should be applied in an inconspicuous location to test the compatibility of the coating with the prepared substrate. Allow the coating to dry and cure fully, then inspect for proper film formation, gloss, adhesion and confirm that the film is free from whitening or any other defects.

MIXING:

The material is ready for use and requires no mixing or dilution. It is unlawful to further dilute with non-exempt solvents.

TECHNICAL DATA

Composition and Materials:	A blend of 100% methyl/methacrylate polymers in a fast drying aromatic solvent. No fillers are used and there are no oils, waxes or saponifiable resins.
Percent Solids:	27.5%
Flash Point:	> 100°F
Moisture Efficiency:	.39 kg/m ² @ 300 ft ² /gallon
Drying Time	
Tack Free:	1 hour
Open to Traffic:	2 hours
VOC Content:	< 700 g/l
A.I.M. Category:	Curing and Sealing Compound Maximum VOC 700 g/l
Applicable Standards:	<ul style="list-style-type: none"> - ASTM C-1315, Type 1, Class A, B & C - ASTM C-309, Type 1, Class A & B and Type 1D with a red dye added - Fed. TTC-C-800A, Type 1, Class 1 - AASHTO Des. M-148, Type 1, Clear - DE CRD - C-300 - USDA Authorization for use in meat, poultry and food processing plants. - Resilient Tile Institute approval for compatibility with most resilient tile, carpet adhesives and paints.

APPLICATION:

TK-BRIGHT GLAZE WILL DARKEN CONCRETE.

Apply with a brush, roller or long nap applicator. Work the compound into the concrete avoiding accumulations, puddling, runs or sags. On large areas, an airless sprayer may be used.

Note that concrete must be fully cured (looks uniform in color) and dry at the time of application. This eliminates the possibility of moisture becoming trapped between the film and the concrete slab, resulting in a white haze on the surface. If a white haze does develop, an application of TK-00 XYLENE* will dissolve the film and allow trapped moisture to escape. TK-BRIGHT GLAZE will then be able to reharden clearly.

CLEAN UP:

Use TK-00 XYLENE* to clean tools and equipment. Pump solvent through the sprayer to remove residue of materials which can clog the hose and wand assembly.

COVERAGE:

Surface	Coverage
Curing Exposed Aggregate:	300-500 sq.ft./gal
Second coat, cured concrete, burnished block:	300-500 sq.ft./gal

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

MAINTENANCE:

Minimal maintenance is required other than occasional sweeping, dusting or mopping. If wear patterns do occur or if spillage removes the coating, TK-BRIGHT GLAZE may be reapplied to the affected area(s).

LIMITATIONS:

- Apply in temperatures above 40°F. Colder weather applications may be made under prescribed conditions and procedures specified by TK Products.
- Follow industry standards for use on colored concrete.
- Not for use on asphalt or surfaces subjected to hydrostatic water pressure, or as a waterproofer on below-grade surfaces.
- Sprayers must be equipped with neoprene hose, washers and gaskets as rubber or other materials will disintegrate from the solvent.
- Material will not freeze and may be stored outdoors in cold weather, however it must be allowed to warm to approximately 50°F before use.

Note 1. Concrete containing calcium chloride will remain dark longer when sealed. Extenders and additives (concrete admixes, fly ash) are now being added to some ready mixed concrete which can cause inconsistency in the porosity of the concrete. Some areas of the finished concrete may then appear darker than others. To compensate for these variations, coverage ratios should be adjusted.

Note 2. Popout problems can occur anytime, however, concrete in certain regional areas, concrete applied in extremely hot conditions (90°F+), and heavily steel troweled concrete can aggravate popout problems. These deficiencies are the result of a heat caused reaction, called alkaline silica reactivity (ASR), between the silica in the shale particles of the fine aggregate with the sodium and potassium alkali in the portland cement. For more information on this problem, refer to "POPOUTS" by Norman E. Henning, P.E. and Kenneth L. Johnson, P.E. of Twin City Testing and Engineering Laboratory and Lowery J. Smith of the J.L. Shiely Company. Where this type of shale is present, and extremely hot weather conditions prevail, it is recommended that liquid membrane curing compounds should not be used until the concrete has been completely cured by water ponding, continuous

water spray mist, or wet burlap covering for a period of three days. A seal coat can then be applied for dustproofing and protection (when concrete is completely dry).

Note 3. When using a liquid or powder release (other than TK-LIQUID STAMP RELEASE 2090) care must be taken to ensure proper washing has taken place prior to applying TK-BRIGHT GLAZE as these substances may affect product adhesion and formation.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK Distributors, the TK office and the TK website.

AVAILABILITY:

TK-BRIGHT GLAZE is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in 55-gallon drums, 5-gallon pails and 1-gallon cans.

FOR PROFESSIONAL USE ONLY

NOTES:

*TK-00 XYLENE must be purchased separately

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

03/18 Last Rev. 11/14

**TK Products Construction Coatings**

11400 West 47th Street Minnetonka, MN 55343

800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com